

TECHNICAL DATA SHEET

ClearBrite® Short Line Brush

Finish Description: ClearBrite® Short Line Brush has a thin anodize film thickness that make it quite versatile for many applications while providing the designer with another alternative to stainless steel. The brushed surface and natural aluminum color provides an elegant finish that simulates the appearance of a brushed stainless steel without the huge price tag.

Reference Part Number (s)

1250-125-012

Industry Designations

Aluminum Association

AA-M12-C30-A21

Mil A-8625F Classification

Type II Sulfuric Anodize

Industry Standards

ISO 9001: 2008

Quality management system

Mil A-8625F Anodizing Standard

Anodic coatings for aluminum and aluminum alloys

Aluminum Properties

Alloy: 5205

Temper: H18

Finish: Short Line (SL) Brushed

Mechanical Properties

UTS: 27 ksi min [186MPa]

YTS: Not specified

Elongation: 1% minimum

T Bend: Recommended 3t minimum

Chemical Properties

Si: 0.15 %

Fe: 0.7 %

Cu: 0.03 - 0.10 %

Mn: 0.10 %

Mg: 0.6 - 1.0 %

Cr: 0.10 %

Zn: 0.05 %

Other: 0.15 %

Al: Remainder

Stock Gauge Availability ¹

0.025" (0.6 mm)

Stock Width Availability ²

48.5" (1232 mm)

Anodize Film Thickness

Decorative Anodic Layer:

0.125 mils [3.2 µm]

Anodize Finish Properties

Optical: Chemically Brightened

Gloss: Not applicable

Color : Natural Aluminum

Color Target: Not applicable

UV Stable: Yes

Environment: Interior ³

Seal: S3, Duplex Seal III

Quality Grade: 2

Other:

Footnotes: 1 - Other gauges can be custom ordered. 2 - Other widths can be custom ordered. 3 - This product is available for exterior use; a minimum film thickness of 0.250 mils (6 µm).



TECHNICAL DATA SHEET

ClearBrite® Short Line Brush

Aluminum Secondary Services

- Shearing, Width Capabilities:**
7" (178mm) - 62" (1575 mm)
- Shearing, Length Capabilities:**
Up to 192" (4876 mm)
- Shearing, Loading Gauge:**
Up to 0.080" (2.0 mm)
- Slitting, Width Capabilities:**
0.75" (19 mm) min
- Slitting, Loading Gauge:**
Up to 0.100" (2.5 mm)
- Other Secondary Services:**
Protective peel-able films
International packaging
Perforating and embossing

Maintenance and Cleaning

The anodized aluminum finish can be washed with mild soap and water followed by a clean water rinse. For more information on cleaning anodized aluminum, please refer to the Aluminum Association Publication 92, Care of Aluminum or AAMA 609 & 610-09, Cleaning and maintenance guide for architecturally finished aluminum.

Sustainability and LEED

- Recycled Content, 5005 alloy:**
100% recyclable
Recycled Content, 6.6%
Reclaimed-Virgin Material, 93.4%
2012.04.30 Mills
- Volatile Organic Compounds:**
The aluminum oxide layer does not contain any VOC's

Availability

The standard lead time for stocked gauges and widths is two weeks for anodizing and one week for any secondary services such as slitting, shearing and applying transparent protective films or paper.

Please check availability of Non-Stocked materials by contacting our sales staff using our toll free number 800.654.1159 or email your request to info@lorin.com. Some raw materials may have extended lead times.

Technical Support

A staff of factory trained personnel are available to offer technical assistance. Please call our toll free number 800.654.1159 or email your question to info@lorin.com.

Product Support Partners

Lorin Industries works very closely with many manufacturers' in multiple markets who specialize in anodized aluminum fabrication. Our support staff can assist you if you are looking for finished components. Please call our toll free number 800.654.1159 or email your request for product and application support to info@lorin.com.

Warranty

A limited warranty may be available upon request. The warranty is issued on a per project basis and can be applied for on line by completing an application for warranty at www.Lorin.com

Anodized Finish Test Data

| Characteristic | Test Method | Standard | Test Results |
|------------------------|---------------------------------|---|--|
| Oxide Layer, Thickness | ASTM B244 - Eddy current method | AA Protective & Decorative coating less than 10.2 µm (0.400 mils) maximum | Nominal Target, 3.2 µm (0.125 mils) |
| Oxide Layer, Weight | ASTM B137 - Coating Dissolution | | > 0.8 mg/cm ² (4.8 mg/in ²) |
| Film Hardness | ASTM 3363 - Pencil Hardness | Based on anodic thickness, 3 µm (0.125 mils) | 4H Hardness |
| Seal Quality | ASTM B136 - Dye Stain | Dye Stain Test | Pass, No Visible Stain |

Copyright and Disclaimer: The information described in this document is proprietary to Lorin Industries Inc. and is made available for information only. The test data contained in this document is the most current test data available at the time of printing. If you have any questions about the content or updated information, please contact us by email at info@lorin.com or call our toll-free number listed below.

◆ Toll Free 800.654.1159 ◆ International 231.722.1631 ◆ www.Lorin.com ◆ info@lorin.com ◆

